

## DINITROL L-142

### Paint Protection

#### Characteristics:

- Milky white
- Protects from chemicals
- Protects from aggressive pollutions
- Removable after exposure

#### Applications:

DINITROL L142 protects the painted metal from UV-radiation, aggressive chemicals and atmospheric pollution, during transport and storage.

Even after one year in heavy conditions, the film is easily removable with an organic degreaser. DINITROL L142 does not affect other details commonly used on cars, such as rubber, plastics and aluminium.

DINITROL L142 has low aromatic content. The product dries in minutes, easily withstanding rain or water splashing.

DINITROL L142 is designed for protection of newly painted cars or other similar painted surfaces. DINITROL L142 can also be used on areas in need of temporary corrosion protection.

#### Method of use:

DINITROL L142 is applied by spraying. It can be sprayed either with high pressure, low pressure or air-mix spraying equipment.

#### Technical properties:

Colour:	transparent
Type of film:	tack-free, waxy
Density at 23°C:	770 kg/m <sup>3</sup>
Viscosity at 23°C (DIN 2 cup):	50 seconds
Dry matter content:	9% by weight
Flash point:	40°C
Recommended film thickness wet:	110 µm
Drying time:	13 mins
Effect on car paint:	none
Removability:	cold Degreaser
Available in:	208 L Drum

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telefon:  
+49 (0) 52 81 / 9 82 98-0  
Telefax:  
+49 (0) 52 81 / 9 82 98-60  
E-Mail:  
service@dinol.com